

המרכיב	עמידות כימית			
	40°C	60°C	80°C	100°C
Monochloro Benzene	D			
Monoethanolamine	A			
Monoethyl Ether	A	A	A	
Monomethyl Aniline	A	A	A	
Morpholine	A	A		
Motor Oil				C
Mowilth	A	A		
Mustard	A	B		
Nafta	B	U		
Naphthalene, Naphthaline	A	C		
Natural gas	A	A		
Nickel	A			
Nickel Chloride	A	B		
Nickel Nitrate	A	B		
Nickel Salts	A	A		
Nickel Sulphate	A	B		
Nicotine	A	A		
Nicotine Acid	B	B		
Nitric Acid <30%	A	A		
Nitric Acid 30-50%	B	C		
Nitric Acid 40%	B			
Nitric Acid 70%	C			
Nitric Acid 98%				U
Nitrobenzene (Oil of Mirbane)	C	U		
Nitrocellulose	A			
Nitroethane	A			U
Nitrogen	A	A	A	
Nitroglycerin	B	D		
Nitromethane	A			U
Nitrotoluene	A	B		
Nitrotoluol	A			B
Nitrous gases, conc.	A			U
Nonyl Alcohol	A	A		
Octane	A	B		
Octyl Alcohol	A			B
Octyl Cresol	B	U		
Oil	C	C		
Oil Acid				C
Oleic Acid	A	C		
Oleic Acid (Red Oil)	U			
Oleum	U			
Oleum vapeur (SO ₃)	B			
Olive Oil	A	A	A	
Optical Brighteners	A	A		
Orange Extract	A	A		
Ortho-Boric Acid	see Boric Acid			
Oxalic Acid	A	B		
Oxyacetic Acid	see Glycolic Acid			
Oxybensole	see Phenol			
Oxydiethanole	see Diethylene Glycol			
Oxygen	A	A		
Oxypropionic Acid	see Lactic Acid			
Oxyrane	see Ethylene Oxide			
l-Oxytoluol	see Benzyl Alcohol			
m-Oxytoluol	see Cresol			
Ozone	C			U
Painting Turpentine	see Thinner			
Palm Kernal Oil	A	A		
Palm Oil	B	B		

המרכיב	עמידות כימית			
	40°C	60°C	80°C	100°C
Palmatic Acid	A	A	B	
Palmyl Alcohol	A	A		
Palmolive Oil	A			
Paraffin	A	B	C	
Paraffin emulsion, trading qual.		B		
Paraffin Oil	A	A	A	
Paraformaldehyde	A	A		
Paratoluene Sulpho Chlora				
Amide Sodium 1%	A			
Peanut Butter	B	B		
Pentanol	see Amyl Alcohol			
Pentanol Acetate	see Amyl Acetate			
Pepper	B	B		
Peppermint Oil	B	D		
Perchloric Acid 10%	A	A		
Perchloric Acid 20%	A	A	A	
Perchloric Acid 50%	A	B	C	
Perchloric Acid 70%	A	D		
Perchloro Ethylene	U			
Perfumes	C	U		
Petrol Ether				C
Petroleum	A	B		C
Petroleum Ether	A	D		
Petroleum Jelly	B	B		
Petroleum Spirits	C	D		
Phenol up to 90%	A	A		U
Phenolic Resins	A	A		
Phenols 100% (Carbolic Acid)	D			
Phenyl Alcohol	see Benzyl Alcohol			
Phenyl Ethane	see Ethyl Benzene			
Phenyl Ethyl Alcohol	A	A		
Phenyl Hydrazine	C	D		
Phenyl Hydrazine Hydrochloride	A	U		
Phenyl Methane	see Toluol			
Phenyl Methyl Ether	see Cyclohexanone			
Phenyl Sulfonate	A	A		
Phosgene, gas	U			
Phosphates	A	A	A	
Phosphoric Acid 80%	A	A	A	A
Phosphoric Acid 90%	A	A	A	A
Phosphoric Acid 95%	A	A		
Phosphorus Oxychloride	A	B	B	
Phosphorus Pentoxide	A	A	A	
Phosphorus Trichloride	A	B		
Phosphorus Yellow	A			
Photographic Developer	A	A		
Photographic solution, Fixer	A	A	A	
Phthalic Acid 50%	A	A	A	
Phtalic Acid Ester	A	C		
Phtalic Anhydride	B	B		
Pickling Baths	B	C		
Picric Acid 1%	A			B
Pine Oil	B	D		
Pineapple Juice	A	A		
Pinene				B
Plasticizers of Polyester	A	B		
Plating Solutions, Brass	A	B		
Plating Solutions, Cadmium	A	B		
Plating Solutions, Copper	A	B		
Plating Solutions, Gold	A	B		

24.7 - 04/2009