

המרכיב	עמידות כימית			
	40°C	60°C	80°C	100°C
Plating Solutions, Indium	A	B		
Plating Solutions, Iron	A	B		
Plating Solutions, Lead	A	B		
Plating Solutions, Nickel	A	B		
Plating Solutions, Rhodium	A	B		
Plating Solutions, Silver	A	B		
Plating Solutions, Tin	A	B		
Plating Solutions, Zinc	A	B		
Polyesters (Resins)	C	U		
Polyglycols	A	A		
Polysolvan O	A	A		
Potash Alum	A	A		
Potassium Acetate			B	
Potassium Bicarbonate	A	B		
Potassium Bichromate 40%	see Potassium Dichromate			
Potassium Bisulphate	A	A		
Potassium Borate 1%	A	A	A	
Potassium Bromate	A	A	A	
Potassium Bromide	A	A	A	
Potassium Carbonate	A	A	A	
Potassium Chlorate	A	A	A	
Potassium Chloride	A	A	A	
Potassium Chromate	A	A	A	
Potassium Chromium Sulphate	A	A	A	B
Potassium Cupro Cyanide	A	A	A	
Potassium Cyanide	A	A	A	
Potassium Dichromate 40%	A	A	A	
Potassium Ferricyanide	A	A	A	B
Potassium Ferrocyanide	A	B		
Potassium Fluoride	A	A	A	
Potassium Hydrogen Carbonate	A	A	A	
Potassium Hydrogen Sulphate	A	A	A	
Potassium Hydrogen Sulphite solution	A	A	A	
Potassium Hydroxide 50%	A	A	A	U
Potassium Hydroxide 60%	A	A	B	
Potassium Hypochlorite, solution	A		B	
Potassium Iodide, cold saturated	A	A	A	
Potassium Nitrate	A	A	A	
Potassium Orthophosphate	A	A	A	
Potassium Perborate	A	A	A	
Potassium Perchlorate 1%	A	A	A	A
Potassium Perchlorate 10%	A			
Potassium Permanganate 18%	A	A	A	
Potassium Persulfate	A			
Potassium Phosphate	A	A	A	
Potassium Salts	A			
Potassium Sulphate	A	A	A	
Potassium Sulphate, cold saturated	A	A	A	
Potassium Sulphide	A	A	A	
Potassium Sulphite	A	A		
Potassium Supersulphate	A	A	A	U
Potassium Tetracyano Cuprate	A	A		
Potassium Thiosulphate	A	A		
Propargyl Alcohol	A			
Propane Acid	see Propionic Acid			
Propane Diol	see Propylene Glycol			
Propane Triol	see Glycerine			

המרכיב	עמידות כימית			
	40°C	60°C	80°C	100°C
Propane, gas	A	B		
Propane, liquid	B			
Propanol	A	A	A	
Propanone	see Acetone			
Propargyl Alcohol	A	B		
Propene	A	A	A	
Propionic Acid	A	A	A	
Propyl Acetate				B
Propyl Alcohol	see Propanol			
Propylene Dichloride	U			
Propylene Glycol	A	A	A	
Propylene Oxide	A	A		
Prune Juice	A			
Pseudo Cumol/Pseudo Cumene	B	B		
Pyridine	A	B		C
Pyrol				B
Quinine	A	A		
Rayon Coagulating Bath	A	B		
Resorcinol	A	B		
Ricine Oil	A			B
Rinser Loosener	A	A		A
Road Tar	U			
Roasting Gases	A	A		
Rouge	A	A		
Rubbers Dispersions/Latex	A	A		
Sagrotan	A	B		
Salicylic Acid	A	A		A
Salicylic Acid Methyl Ester	A	B		
Sauerkraut	A	A		
Sea Water	A	A		
Selenic Acid	A	A		
Shampoos, Shaving Lotion	A	A		
Shortening	A	B		
Silicic Acid	A	A		
Silicone Fats	A	A		A
Silicone Oils	A	A		A
Silver Nitrate <80%	A	A	A	B
Silver Salts, cold saturated	A	A	A	
Soap	A	A	A	
Soap Loosener	A	A	A	
Soap Solution	A	A	A	
Soda	see Sodium Carbonate			
Sodium Acetate	A	A	A	
Sodium Aluminate	A	A	A	
Sodium Aluminium Sulphate	A	A	A	
Sodium Benzoate	A	A	A	
Sodium Benzoate to 36%	A	A	A	
Sodium Bicarbonate	A	A	A	
Sodium Bisulphate	A	A	A	
Sodium Bisulphite	A	A	A	A
Sodium Borate	A	A	A	
Sodium Bromide	A	A	A	
Sodium Carbonate	A	A	A	
Sodium Chlorate	A	A	A	
Sodium Chloride	A	A	A	A
Sodium Chlorite 50%	A			
Sodium Chlorite and Bleach	A			B
Sodium Chlorite and Water	A			
Sodium Chromate	A	A		