

המרכיב	עמידות כימית			
	40°C	60°C	80°C	100°C
Trinitro Phenol	see Picric Acid			
Trinitro Toluene	U			
Trioctyl Phosphate	A	B		
Trisodium Phosphate	A	B	C	
Trybutyl Phosphate	A	A	A	
Turbine Oil			B	
Turpentine	D	U		
Tutogen U	A	A		
Tween 20	B	U		
Tween 80	B	U		
Urea	A	B		
Uric Acid	A	A		
Uric Compounds	see Carbamide			
Urine	A	A		
Urine, normal conc.	A	A	A	
Vanille Extract	A	B		
Vaseline	A	B	C	
Vaseline Oil	A		B	
Vegetable Dyes	A	A		
Vegetable Oils	B	B	B	
Vinegar	A	A	A	
Vinegar Acid Anhydride	A	A	B	U
Vinegar Acid Butyl Ester	see Butyl Acetate			
Vinegar Acid Ethyl Ester	see Ethyl Acetate			
Vinegar Ester	see Ethyl Acetate			
Vinegar, trading quality	A	A	A	
Vinyl Acetate	A	A		
Vinyl Chloride	A	A	A	
Vinyl Cyanide	see Acryl Nitrite			
Viscose Spinning Solution	A	A		
Vitamine C	A	A		
Walnut Oil	A	B		
Wastegases with Acid	A	A		
Wastegases with Carbon Monoxide	A	A		
Wastegases with HCL	A	A		
Wastegases with H2SO4	A	A		
Wastegases with low sodium Dioxide	A	A		
Wastegases with traces of Hydrogen Fluoride	A	A		
Wastegases with traces of Nitrosyl Sulfuric Acid	A	A		
Water	A	A	A	A
Water Acid Mine	A			
Water Deionized	A			
Water Distilled	A			
Waterglass	A			
Waxes	A	C		
Wetting Agents	A	B		
Whey	A	A		
Whisky	see Ethyl Alcohol			
Whitener	see Sodium Hypochlorite			
Wine Vinegar	see Vinegar			
Wine, red and white	A	A	A	
Wohlstone Acid	A	A	A	
Wood Glue, type Polyvinyl Acetate	B			
Wood Stains	A	C		

המרכיב	עמידות כימית			
	40°C	60°C	80°C	100°C
Wool Fat	see Lanolin			
Xylol	C			U
Yeast	A	A	A	
Zinc Bromide	A	A		
Zinc (II) Chloride	A	A	A	B
Zinc Carbonate	A	A	A	
Zinc Hydrate	A	A	A	
Zinc Oxide	A	A	A	
Zinc Salts	A			
Zinc Sludge	A	A		
Zinc Stearate	A	A		
Zinc Sulphate	A	A	A	